Water-Activated Leak Sealing Kit





Belzona 9631 is a leak-sealing kit containing a 5cm x 150cm / 2in x 60in fiberglass pre-impregnated wrap which is activated by water. Packaged in a hermetically sealed foil pouch, it is ready to use and does not require any measuring or mixing.

It is odourless and very simple to apply. This material bonds well to copper, steel, SS, PVC and many other substrates. Belzona 9631 is a versatile solution for industries where quick-action pipe repairs are critical.

| Working life: | 1.5min at 40°C/104°F | 3min at 20°C/77°F |
|---|---|--|
| | 6min at 10°C/50°F | 12min at 5°C/41°F |
| Tensile shear adhesion: Tensile shear adhesion (Immersion): | Wet /dry mild steel: 990/750psi (6.8/5.2MPa) | Wet /dry copper: 850/330psi (5.9/2.3MPa) |
| | Wet/dry SS: 1949/980psi (7.2/6.8MPa) | Wet/dry GRP: 0/360psi (3.4/2.5MPa) |
| Tensile shear adhesion (Immersion): | 1170 psi / 8.1 MPa after 1000 hours immersion at 40°C/104°F | |
| Heat resistance (HDT): | 66°C/150°F at 20°C/68°F | |
| Flexural strength: | 23.8 x 103/165MPa | |
| Pressure retention capability: | On a 76mm/3-in dia pipe, prepared to SSPC-SP11, with a defect up to 6mm diameter, typical value for Belzona 9631 tested as a nine-layer wrap will be 100 psi/7 bar. | |
| Shelf life: | 2 years | |
| | Tensile shear adhesion: Tensile shear adhesion (Immersion): Heat resistance (HDT): Flexural strength: Pressure retention capability: | Working life: Tensile shear adhesion: Wet/dry mild steel: 990/750psi (6.8/5.2MPa) Wet/dry SS: 1949/980psi (7.2/6.8MPa) Tensile shear adhesion (Immersion): 1170 psi / 8.1 MPa after 100 do C/104°F Heat resistance (HDT): 66°C/150°F at 20°C/68°F Flexural strength: 23.8 x 103/165MPa Pressure retention capability: On a 76mm/3-in dia pipe, with a defect up to 6mm do Belzona 9631 tested as a nipsi/7 bar. |

Kit Contents:

- Gloves
- Surface roughing mesh
- Cleaning wipes
- Water-activated wrap in a sachet
- Release film

Cure Times:

Belzona 9631 will be hard in 60-90 minutes at 68°F (20°C) but curing will take longer in dry climates or cold temperatures.



READY TO USE NO MIXING



HEAT RESISTANT



QUICK RETURN TO SERVICE



PRESSURE RESISTANT

9000 Series


BELZONA 9631



Step-By-Step Application:



1. Roughen and clean surface



2. Soak wrap



3. Apply wrap



4. Apply film



5. Application complete



Watch application video:

Watch on BelzonaTV

Application Areas:

- Corroded pipes
- Cracked pipes
- Force mains
- Gravity lines
- Irregular pipe fittings
- Leaking pipes



Kit contents (left to right) gloves, release film, roughing brush, cleaning wipes, water-activated wrap in a sachet

For more information, please contact your local Belzona representative:

QUALITY PRODUCTS - TECHNICAL SUPPORT

Belzona products are manufactured under an ISO 9001 Registered Quality Management System.

Belzona has a global distribution network of over 140 Distributors operating in 120 countries. Local support is provided by a trained Technical Consultant who will diagnose the problem, recommend the solution and provide 24-hour, on-site application supervision and advice.